



thermoset high-performance insulating material

application	for universal use in the insulation and construction area and thermal insulation of technical facilities	
assembly	unlaminated blocks, boards or pre-cut parts dimensions at customer's option upon request dimensional tolerances acc. to puren factory standard	

puren-PIR NE 36 **Technical data PU rigid foam**

Characteristic	Standard/test procedure	Unit	Indicator
Material	Polyurethane rigid foam (PU) acc. to EN 13165 and EN 14308, quality-certified, harmless from a biological and building ecology point of view, recyclable, rotproof, resistant to mildew and decay.		
Bulk density	EN 1602	kg/m ³	35 - 39
Thermal conductivity			
Monitored limit value (fresh value) at 10°C mean temperature	EN 12667	W/(m·K)	0,021
Nominal value (EU) λ_D			at thickness
	EN 13165		d < 80 mm
	EN 14308	W/(m·K)	80 ≤ d < 120 mm
			d ≥ 120 mm
			0,027
			0,026
			0,025




Thermal insulation resistance for thickness	mm	20	40	60	80	100	120	140	160	180	200
R_D	m ² ·K/W	0,70	1,45	2,20	3,05	3,80	4,80	5,60	6,40	7,20	8,00

Compressive strength			measured values ²⁾
Compressive stress at 10% compression	EN 826	kPa	150
E-modulus (compressive stress) ²⁾		MPa	240 - 280
Tensile strength perpendicular to panel plane			
Transverse tensile strength	EN 1607	kPa	100
E-modulus (transverse tensile stress) ²⁾		MPa	220 - 270
Bending strength ²⁾	EN 12089	kPa	300 - 400
Transverse strength ²⁾	EN 12090 (in compliance with DIN 53427)	kPa	120 - 160
Shear strength ²⁾	EN 12090 (in compliance with DIN 53294)	kPa	150 - 190


Designation (EU)	EN 13165	PU-EN 13165-T2-DS(70,90)3-DS(-20,-)2-CS(10/Y)150-TR100
	EN 14308	PU-EN 14308-DS(TH)3-CS(10/Y)150

Fire behaviour	non-smouldering, non-melting, non-dripping	
Reaction to Fire Class / RtF (EU)	EN 13501-1	E

1) Literature value, not part of the factory production control and external supervision.
 2) Average values calculated on a regular basis under production conditions as part of factory production control.
 It is ensured that mechanical characteristic values do not fall below their minimum level by more than 10%..



Declaration of performance
 20121.CPR.2020.10
 puren-PIR NE 32
www.puren.com/download



EN 13165:2012+A2:2016
 EN 14308:2015
 Verification authority: 0751 FIW München



controlled by
 0751 FIW München

thermoset high-performance insulating material

puren-PIR NE 36		Technical data PU rigid foam		
Characteristic		Standard/test procedure	Unit	Indicator
Closed cell content ²⁾		ISO 4590	%	90 - 95
Temperature resistance			°C	-30 bis +120, short-term to 250 °C
Moisture absorption ²⁾		EN 12087	Vol.-%	≤ 3
Specific heat capacity ¹⁾	C	EN 12524	J/(kg·K)	1400
Water vapour diffusion resistance factor ¹⁾	μ	EN 12086		40 - 200
Linear expansion coefficient ¹⁾		EN 1604	1/K	5 - 8 · 10 ⁻⁵